Instructions for Use Screed additive Temporex



for Fonterra radiant heating and cooling, cement screed, faster setting, improvement in the screed quality



Year built (from) 01/2007



INT

Table of contents

About these instructions for use 3 1.1 Target groups 3 1.2 Other applicable documents 3 1.3 Labelling of notes 3 Product information 5

| 2.1 Standards and regulations | 5 |
|------------------------------------|---|
| 2.2 Safety advice | 5 |
| 2.3 Intended use | 6 |
| 2.4 Features and mode of operation | 6 |
| 2.5 Technical data | 7 |

Handling83.1 Transport and storage83.2 Guide mixture83.3 Disposal9

1 About these instructions for use

Trade mark rights exist for this document, further information can be found at *viega.com/legal*.

1.1 Target groups

The information in this instruction manual is directed at the following groups of people:

- Heating and sanitary professionals and trained personnel
- Screed installer

It is not permitted for individuals without the abovementioned training or qualification to mount, install and, if required, maintain this product. This restriction does not extend to possible operating instructions.

The use of Viega products must be carried out in accordance with the general rules of engineering and the Viega instructions for use.

1.2 Other applicable documents

Safety data sheet screed additive Temporex in acc. with 1907/2006/EC

For the safety data sheet, refer to the respective product page in the online catalogue.

1.3 Labelling of notes

Warning and advisory texts are set aside from the remainder of the text and are labelled with the relevant pictographs.



DANGER!

This symbol warns against possible life-threatening injury.



WARNING! This symbol warns against possible serious injury.



CAUTION!

This symbol warns against possible injury.





NOTICE!

This symbol warns against possible damage to property.



Notes give you additional helpful tips.

2 Product information

2.1 Standards and regulations

The following standards and regulations apply to Germany / Europe. National regulations can be found on the relevant web site of your country at *viega.com/standards*.

Regulations from section: Intended use

| Scope / Notice | Regulations applicable in Ger- many |
|--|--|
| Cement and calcium sulphate heating screeds | DIN EN 13813 |
| Screeds in the building trade | DIN 18560 |
| Installation of underfloor heating | DIN EN 1264-4 |

Regulations from section: Suggested formulations

| Scope / Notice | Regulations applicable in Ger- many |
|-----------------------------|--|
| Cement / cement composition | EN 197-1 |
| Aggregate | DIN EN 206-1 |
| | DIN 1045 |

Regulations from section: Disposal

| Scope / Notice | Regulations |
|--------------------------------|-----------------------------------|
| Disposal as construction waste | Abfallschlüssel TA-Abfall: 31 309 |

2.2 Safety advice



DANGER! Causes skin irritation and severe damage to the eyes

Avoid contact with the eyes and skin.

- In case of contact with eyes, rinse thoroughly for a number of minutes.
- If possible, remove contact lenses, if worn.
- If necessary, contact a doctor.





DANGER! Risk to health Keep out of the reach of children.

NO Obse cher

NOTICE! Observe the normal safety measures when dealing with chemicals.

- Protect yourself with working clothes and gloves.
- Wear eye protection and a face mask.

2.3 Intended use

Additive for the production of cement screeds for use in connection with underfloor heating; also refer to \Leftrightarrow *Regulations from section: Intended use' on page 5.* Improves the screed quality and binds quicker.

System components for CE mortar CT - C25 - F \ge 4.

The screed hardnesses are mainly dependent on the proper mortar mixture, the technically correct laying and the quality of subsequent treatment.

2.4 Features and mode of operation

Screed additive Temporex reduces the required amount of added water and simultaneously raises the level of flexibility of the fresh mortar. Alongside quicker drying, the reduction of the water content in the fresh mortar causes an increase in the bending tensile strength and compressive strength.

Additives are employed with the aim of positively influencing plastification, pumpability, binding, hardening and drying behaviour. They are not a substitute for unsuitably or incorrectly mixed screed mortars.

The drying time is mainly dependent on the thickness of the screed, the amount of water added and the climatic conditions. No other additives may be added to the screed when using screed additive Temporex.

NOTICE!

The residual humidity of the heating screed should be checked (CM measurement) by the subsequent tradesperson (normally the floorer) before the work of covering the floor is begun.



2.5 Technical data

Hardening time

Can be walked upon after

| 300 g/m ² at 45 mm pipe coverage and up to 2 kN/m ² | ; |
|--|---|
| 10 days | |
| 2 days | |



3 Handling

3.1 Transport and storage

Observe the following with transport and storage:

- Store in a frost-free place without direct sunlight.
- Can be stored in the closed canister for up to twelve months from the production date.
- Mix or shake before use.
- Delivery form: 10 kg plastic canister

3.2 Guide mixture



NOTICE!

We recommend protecting the hands (with skin cream containing fat or protective gloves) in accordance with the pertinent health and safety regulations.

Raw materials

| cement * | CEM I 32.5 R |
|--------------|---|
| aggregate * | 0/8 mm, wire line A/B |
| Water | Mains water |
| Additive | Screed additive Temporex |
| Dosage | 2-3 % of the cement weight |
| Mixing ratio | Cement (aggregate mixture): approx. 1:5–1:6 (quantity ratio) (50 kg cement : approx.275 kg supplement) |
| | Cement content: ≥ 280–300 kg/m ³ |
| | Aggregate: approx. 1680–1700 kg/m ³ |

* according to applicable regulations, see \Leftrightarrow 'Regulations from section: Suggested formulations' on page 5

Order of dosage (addition in 200 I pull mill or supply mixer)

| Aggregate 0/8 | 1/3 |
|--------------------------|----------|
| Cement CEM I 32.5 R | 50 kg |
| Screed additive Temporex | 1–1.25 l |

| Mixing water | approx. 10 l |
|--|------------------|
| Aggregate 0/8 | approx. 2/3 |
| Mixing water (depending on the individual wetness of the supple- ment) | 5–10 l |
| Mortar consistency | plastic to stiff |
| | |

3.3 Disposal

Separate the product and packaging materials (e. g. paper, metal, plastic or non-ferrous metals) and dispose of in accordance with valid national legal requirements.

Mix residue with cement and dispose of as builders' waste after setting pursuant to the applicable regulations: also refer to \Leftrightarrow *'Regulations from section: Disposal' on page 5*. The packaging can be re-used or recycled after cleaning.



INT • 2022-08 • VPN170561

